

ROLLED RUBBER SEALER INSTRUCTIONS:

Clean rubber flooring well – vacuum, sweep, then clean use a damp sponge mop (if needed) and a properly diluted neutral ph cleaner and let dry completely.

Shake the sealer well before opening.

Apply a very thin coat of Rubber Mat Sealant – (for E-Finish brand you will get about 1,000 sq ft per gallon coverage for the 1st coat. For the SLX Brand Sealer, you will get 2,500 to 3,000 sq ft per gallon coverage on both the 1st coat and the 2nd coat.) Let dry to the touch.

Apply second thin coat – when using E-Finish brand you will cover about 2,000 sq. ft. for 2nd coat.

We recommend no more than 2 coats of sealer.

Allow no traffic on the floor after 2nd coat for a minimum of 24 hours. Coating will develop full strength in 7 days but can be used normally after allowing it to dry/cure for 24 hours. For best results lightly spray onto the clean, dry rubber flooring using a pump type garden sprayer, then spread uniformly using a paint pad; PADCO type applicator, or the thinnest nap paint roller available. Maintain by periodic cleaning using a vacuum and a damp sponge mop with neutral pH cleaner. Most people choose to apply 1 thin layer of sealer approx. every 12 months.